

## DuPont™ Tyvek® 1460C

### Product Properties—Metric Units

**Product Features:**  
**Corona Treatment**  
**Contains UV Stabilizer**

#### Specification Properties (Metric Units)

Property	Comparable Test Method	Units	Tyvek® 1460C
Basis Weight	ASTM D3776 <sup>1</sup>	g/m <sup>2</sup>	59.0 [56.5–61.5]
Tensile Strength, MD	ASTM D5035 <sup>2</sup> EN ISO 1924 <sup>2</sup>	N/2.54 cm	74 [66–82]
Delamination	ASTM D2724 <sup>3</sup>	N/2.54 cm	0.35 [0.15–0.50]

Notes: Specification properties are based on roll averages from samples taken uniformly across the sheet. Specification properties are controlled to a nominal value and released within specification; the ranges listed represent the controlled minimum and maximum values in which the product is released. The customer is responsible for determining that Tyvek® is suitable for the intended application.

1. Sample size 100 cm<sup>2</sup>
2. Modified for speed, sample width, and gauge length
3. Modified for speed and sample width

Tyvek® styles that contain UV stabilizers do so to extend the service life versus un-stabilized Tyvek® on UV exposure. Specification of UV service life is the responsibility of the customer, as it is heavily dependent on the application and method of use.

#### Miscellaneous Properties (Metric Units)

Property	Comparable Test Method	Units	Tyvek® 1460C
Tensile Strength, CD	ASTM D5035 <sup>2</sup> EN ISO 1924 <sup>2</sup>	N/2.54 cm	65
Thickness	ASTM D1777 <sup>4</sup> EN ISO 534 <sup>4</sup>	µm	190
Mullenburst	ISO 2758 (01)	kPa	540
Gurley Hill Porosity	TAPPI T 460 (06) <sup>5</sup>	sec	85
Hydrostatic Head	DIN EN 20811 (1992) <sup>6</sup>	cm H <sub>2</sub> O	155

Notes: Miscellaneous properties are typical values based on roll averages from samples taken uniformly across the sheet. Miscellaneous properties are not controlled in the process; therefore, they are subject to slight change from normal process drift.

2. Modified for speed, sample width, and gauge length
4. Area = 2 cm<sup>2</sup>; pressure = 50 kPa
5. Pressure: 20 kPa, electronic device
6. Rate of use: 60 cm H<sub>2</sub>O/min

MD = machine direction; CD = cross direction.

**For more information, connect with us at: [www.graphics.dupont.com](http://www.graphics.dupont.com)**

This information is based upon technical data that DuPont believes to be reliable. It is subject to revision as additional knowledge and experience are gained. DuPont makes no guarantee of results and assumes no obligation or liability in connection with this information. It is intended for use by persons having technical skill for evaluation under their specific end-use conditions at their own discretion and risk. Since conditions of use are outside our control, WE MAKE NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATIONS, NO WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE AND ASSUME NO LIABILITY IN CONNECTION WITH ANY USE OF THIS INFORMATION.

This information is not intended as a license to operate under or a recommendation to infringe any patent or technical information of DuPont or others covering any material or its use.

©2019 DuPont. All rights reserved. DuPont™, the DuPont Oval Logo and all trademarks denoted with ™ or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.

## DuPont™ Tyvek® 1460C

### Product Properties—English Units

**Product Features:**  
**Corona Treatment**  
**Contains UV Stabilizer**

#### Specification Properties (English Units)

Property	Comparable Test Method	Units	Tyvek® 1460C
Basis Weight	ASTM D3776 <sup>1</sup>	oz/yd <sup>2</sup>	1.74 [1.65–1.81]
Tensile Strength, MD	ASTM D5035 <sup>2</sup> EN ISO 1924 <sup>2</sup>	lb <sub>f</sub> /in	16.6 [14.8–18.4]
Delamination	ASTM D2724 <sup>3</sup>	lb <sub>f</sub> /in	0.08 [0.03–0.11]

Notes: Specification properties are based on roll averages from samples taken uniformly across the sheet. Specification properties are controlled to a nominal value and released within specification; the ranges listed represent the controlled minimum and maximum values in which the product is released. The customer is responsible for determining that Tyvek® is suitable for the intended application.

1. Sample size 100 cm<sup>2</sup>
2. Modified for speed, sample width, and gauge length
3. Modified for speed and sample width

Tyvek® styles that contain UV stabilizers do so to extend the service life versus un-stabilized Tyvek® on UV exposure. Specification of UV service life is the responsibility of the customer, as it is heavily dependent on the application and method of use.

#### Miscellaneous Properties (English Units)

Property	Comparable Test Method	Units	Tyvek® 1460C
Tensile Strength, CD	ASTM D5035 <sup>2</sup> EN ISO 1924 <sup>2</sup>	lb <sub>f</sub> /in	14.6
Thickness	DIN EN ISO 534 (04) <sup>4</sup>	mils	7.5
Mullenburst	ISO 2758 (01)	psi	78.3
Gurley Hill Porosity	TAPPI T 460 (06) <sup>5</sup>	sec	85
Hydrostatic Head	DIN EN 20811 (1992) <sup>6</sup>	inches H <sub>2</sub> O	61

Notes: Miscellaneous properties are typical values based on roll averages from samples taken uniformly across the sheet. Miscellaneous properties are not controlled in the process; therefore, they are subject to slight change from normal process drift.

2. Modified for speed, sample width, and gauge length
4. Area = 2 cm<sup>2</sup>; pressure = 50 kPa
5. Pressure: 20 kPa, electronic device
6. Rate of use: 60 cm H<sub>2</sub>O/min

MD = machine direction; CD = cross direction.

For more information, connect with us at: [www.graphics.dupont.com](http://www.graphics.dupont.com)

This information is based upon technical data that DuPont believes to be reliable. It is subject to revision as additional knowledge and experience are gained. DuPont makes no guarantee of results and assumes no obligation or liability in connection with this information. It is intended for use by persons having technical skill for evaluation under their specific end-use conditions at their own discretion and risk. Since conditions of use are outside our control, WE MAKE NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATIONS, NO WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE AND ASSUME NO LIABILITY IN CONNECTION WITH ANY USE OF THIS INFORMATION.

This information is not intended as a license to operate under or a recommendation to infringe any patent or technical information of DuPont or others covering any material or its use.

©2019 DuPont. All rights reserved. DuPont™, the DuPont Oval Logo and all trademarks denoted with ™ or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.